



VAPPRO 843 ODOURLESS V.C.I. POWDER

NATO STOCK NUMBER:
PENDING

OVERVIEW

Vapro 843 is an odourless VCI powder specially developed to inhibit ferrous and metal from corrosion after hydrotest. It eliminates formation of corrosion due to residual water after draining hydrotest water. Vapro 843 eliminates the need to force dry the piping system after pressure testing and flushing. Reduces downtime caused by formation of corrosion in piping system which can result in seized valves, blocked pipework and potential damage to downstream process equipment.

Vapro 843 is also an excellent product for dry corrosion protection of metals in recessed areas, interior cavities and voids.

AREAS OF USE

- Hydroblasting, hydrostatic testing.
- Tanks and casing.
- Tubulars, structures, Boiler Pipework.
- Heat exchangers.
- Additive to standing water.
- Process pipework and vessels.

ADVANTAGES

- Essentially non-toxic.
 - Easy to apply.
- Excellent corrosion inhibitor for ferrous metal.
- Does not contain chromates and heavy metals.
- Does not contain ODS (Ozone Depleting System).
- Little or no surface preparation required.
- Protected products can be shipped to customer without removing of water or powder for dry corrosion protection of metals.
- Biodegradable.
- Environmental friendly.
- Eliminates formation of corrosion due to residual water.





PROCEDURE FOR INCORPORATING VAPPRO 843 VCI POWDER INTO HYDROTEST WATER

- Calculate the volume of the system to be hydrostatically pressure tested.
- Add Vapro 843 VCI Powder to test water at a rate of 0.5% to 1% by weight depending on the humidity and salinity of the environment.
- Agitate the mixture for even dispersion.
- Carry out pressure test.
- Drain down system and seal all vents.

PROCEDURE FOR DRY CORROSION PROTECTION OF TUBULARS

- Protects up to 1 cu ft(28 litres) per 30 grams of powder.
- Calculate the volume of the structure to be preserved. By means of a spray gun, fog the desired amount of Vapro 843 and seal all vents.

SPECIFICATIONS

Form
Powder

Appearance
White Powder

Solubility In Water
Appreciable (55 grams in 100 grams at 20°C)

Density
45-50 lbs / cu. ft.

Odour
Odourless

Special Labeling
N.A.

pH
9 ± 0.5(1% aqueous solution)

AVAILABLE PACKAGING

25kg pail

For more information about the product or any technical support, please contact us or our authorized distributor:



HEADQUARTERS, SINGAPORE

Magna International Pte Ltd
10H, Enterprise Road, Singapore 629834.
Tel (65) 6788-1228
Fax (65) 6785-1497
Email info@magnachem.com.sg
Website <http://www.magnachem.com.sg>

NORTH AMERICA

1450 Government Road West
Kirkland Lake, Ontario P2N 2E9
Canada
Email magna@vapro.com
Website: <http://www.vapro.com>



Magna and Vapro are registered trademarks of Magna International Pte Ltd.

Copyright 2006. The details of our products are given completely free of undertaking. Since their application lies outside our control, we cannot accept any liability for the results. User shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.